


# Thermal Interface Material Thermally Conductive Pad



## MATERIAL

Ceramic particle filled silicone rubber sheet




## FEATURES


- Thermally conductive 3.0 W/m-K material
- Available in Standard, Ultrasoft, or Übersoft compression options
- Sheet stock or cut to specification

GP-5000 SERIES PROPERTIES	TEST METHOD	STANDARD (H1)	ULTRASOFT (H0)	ÜBERSOFT (HU)
Softness	ASTM D2240	46 Shore OO	36 Shore OO, starts at 0.50 mm	26 Shore OO, starts at 0.75 mm
Thermal Impedance @ 1.0mm @ 50 psi	ASTM D5470 Modified	0.522 °C-in <sup>2</sup> /W	0.404 °C-in <sup>2</sup> /W	0.385 °C-in <sup>2</sup> /W
Thermal Conductivity				
Thickness	ASTM D374	0.13 mm to 10 mm		
Naturally Tacky		Standard on both sides		
Volume Resistivity	ASTM D257	>10 <sup>14</sup> Ohm-cm		
Dielectric Strength	ASTM D149	10 kV <sub>AC</sub> /mm		
Operating Temperature	TGA+DMA	-55 to 200 °C		
Flammability Rating	UL 94	V-0 (UL File E333972)		
Density	ASTM D792	2.90 g/cm <sup>3</sup>		
Composition		Filled silicone elastomer sheet		
Color	Visual	Light Blue		
Material Option(s)	AO - Hardened skin on one side reducing natural tacky properties	SPAO - Spraying Boron Nitride powder to remove the natural tackiness	G - Hardened skin with fiberglass-woven reinforcement on one side	


Stress Vs. Strain of GP5100-H1/H0/HU (1.0mm thick) with Constant Rate of Strain  
(@ Temp=25-29°C; Constant Rate of Strain = 0.01 inch/min)



Stress Vs. Strain of GP5100-H1/H0/HU (1.0mm thick) with Step Application of Strain  
(@ Temp=25-29°C; Rate of Strain = 0.01 inch/min between each step application of strain; stress measurement time interval of 2 min for each step application of strain)



Thermal Impedance Vs. Stress of GP5100-H1/H0/HU (1.0mm thick) (at Temp=60°C; Step application of pressure 10, 30, 50, 70 psi; ASTM D5470 modified)



## GET IN TOUCH

EMAIL: [SUPPORT@TENNMAX.COM](mailto:SUPPORT@TENNMAX.COM)

TEL: +1 360-567-0707



TENNMAX.COM

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery. V1